

Flowlok AL30 INSTALLERS' GUIDE

Packaging	4.4-gallon kit: One 5-gallon pail, net 4.0 gallons of Side-A and one 0.5 gallon can, net 0.4 gallons of Side-B.
Coverage	FLOWLOK AL30 may be applied at any rate to achieve desired thickness. Theoretical coverage for 15 mil thickness is one gallon per 100 sq. ft.
Mixing	<p>NOTE: FLOWLOK AL30 may NOT be diluted under any circumstances.</p> <p>DO NOT ESTIMATE, proportions are premeasured.</p> <p>Using a mechanical mixer, first pre-mix separately Side-A material thoroughly to obtain an uniform color, making sure to scrape the solids from the bottom and sides of the pail.</p> <p>Pour Side-B into Side-A slowly and while mixing, scrape the sides of the container. Mix for 1-2 minutes. Box the materials. Mix the combined Side-A and Side-B mixture thoroughly until uniform color is obtained.</p>
Application	<p>For best results use a squeegee or notched trowel to spread FLOWLOK AL30 evenly over the entire deck. FLOWLOK AL30 should be applied at a temperature of 20°F and above. Curing time will depend on temperature.</p> <p>For a faster curing time, heat FLOWLOK AL30 to 100 105°F and mix with a static mixer. Dispense FLOWLOK AL30 using a 10:1 ratio dispensing unit. Pour onto the substrate and spread with squeegee and back roll evenly over the entire deck.</p>
Equipment Clean Up	Equipment should be cleaned with an environmentally safe, Urethane grade solvent (alcohol free) as permitted under local regulations immediately after use.
Storage	FLOWLOK AL30 has a shelf life of one (1) year from date of manufacture in factory sealed containers.
Limitations	Do not open until ready to use. Any off ratio mixing of the product will affect the properties and the product may not cure.
WARNING	THIS PRODUCT CONTAINS ISOCYANATES AND CURATIVE MATERIAL.
Chemical Resistance	ASTM D-1308 AND ASTM D-543-95 7 DAY IMMERSION @ 77° F (25° C)

R: Recommended
C: Caution

10% TSP - R	GASOLINE - R
20% AMMONIUM NITRATE - R	HYDROCHLORIC 10% - C
20% SODIUM CHLORIDE - R	ISOPROPANOL - C
ACETIC ACID 10% - C	JET FUEL - R
AMMONIUM HYDROXIDE 10% - R	MEK - C
BLEACH - R	MINERAL SPRITS - R
BRAKE FLUID - R	MOTOR OIL - R
CITRIC ACID 10% - C	OLEIC - R
CHLORINE - R	PMA - C
D-LIMONENE - R	SKYDROL 500B - R
ETHYLENE GLYCOL - C	SKYDROL LD4 - R
	SODIUM HYDROXIDE 50% - R

Warranties

Contact Flowlok for warranty period and information.

CONTACT:

info@flowlok.com

Exclusive distribution and
authorized installation in
Northeastern United States by
DripDrop Waterproofing



www.flowlok.com

BESSERN Building Products
1400 North Providence Road, Media PA 19063
Tel: 484-234-5035 • Fax: 484-234-5037