

Flowlok PLRM SPRAY APPLIED INSTALLERS' GUIDE

Packaging	<p>10-gallon kit: One 5-gallon pail of Side-A and 5 gallon pail, of Side-B.</p> <p>100-gallon kit: One 55-gallon drum, net 50 gallons of Side-A and one 55-gallon drum, net 50 gallons of Side-B.</p>
Coverage	<p>FLOWLOK PLRM may be applied at any rate to achieve desired thickness. Theoretical coverage for 120.0 mil thickness is one gallon per 13.33 sq. ft.</p>
Mixing	<p>NOTE: FLOWLOK PLRM may NOT be diluted under any circumstances. Both the A-side and B-side drums/pails should be pre-mixed prior to use.</p>
Application	<p>FLOWLOK CS primer is recommended on all substrates, except on properly prepared steel (immersion service requires a primer).</p> <p>Prior to application: Precondition both Part-A and Part-B to 75 °F - 80°F (24°C - 27°C) before applying. Ensure that the outside temperature is at least 5°F above the dew point. Fit Part - A with a desiccant drying device.</p> <p>Apply FLOWLOK PLRM using plural component, high pressure spray mixing equipment. FLOWLOK PLRM should be sprayed in a smooth pattern, to establish uniform thickness and appearance. Perform a substrate adhesion test (if required) seven days after application of FLOWLOK PLRM.</p>
Equipment Clean Up	<p>Equipment should be cleaned with an environmentally safe, urethane-grade solvent (alcohol free) as permitted under local regulations immediately after use.</p>
Storage	<p>For FLOWLOK PLRM has a shelf life of one (1) year from date of manufacture in factory sealed containers.</p>
Limitations	<p>Do not open until ready to use. Any off ratio mixing of the product will affect the properties and the product may not cure.</p> <p>FLOWLOK PLRM should be top coated when exposed to heavy pedestrian or vehicular traffic or direct UV exposure. See FLOWLOK AL30 PDS.</p> <p>The end user should check the suitability of this product prior to its application.</p> <p>Excess moisture vapor in concrete slabs may result in primer and/or coating to delaminate, discolor or cause improper curing.</p> <p>Recoat FLOWLOK AL30 within 0 – 12 hours of previous coat (if needed).</p>
WARNING	<p>THIS PRODUCT CONTAINS ISOCYANATES AND CURATIVE MATERIAL.</p>
Warranties	<p>Contact Flowlok for warranty period and information.</p>

FLOWLOK